

DESCRIPTION

Roofcryl is a single component water based 100% acrylic smooth waterproof coating.

ADVANTAGES

- 100% acrylic to protect and waterproof commercial and residential buildings
- Breathable to allow water vapor to escape
- Excellent adhesion, bonds securely to concrete and metal substrate for long-term durability
- Low VOC content for broad compliance across all regions
- Water repellent.
- Highly UV resistance.
- Highly resistance to Cl⁻ ions and CO₂ gas.
- Easy to apply and dries quickly.
- Penetration into concrete is very well.
- Highly resistance to chemicals.
- Excellently adheres on concrete and metal.
- Requires no lining.



APPLICATION

- Once the mixing is ready apply two-coat system, achieving a total dry-film thickness (DFT) (0.3–0.4 mm).
- Apply Roofcryl by brush, spray, roller, or spray-and-backroll.

Roller

- Use a quality ¾ – 1 ¼ nap roller cover.
- Completely saturate the roller and keep it loaded with the coating to build the required mils. Never dry roll.
- Cross roll, maintaining a wet edge, to achieve uniform thickness. Backroll in one direction for consistent appearance.

Brush

- Application by brush is recommended only for small inaccessible areas, (e.g., on touch-ups.)
- Use only a nylon brush.

TECHNICAL DATA

PROPERTIES	RESULTS	TEST METHOD
Density, lbs/gal (kg/L)	11.3–12.3 (1.35–1.47)	ASTM D 1475
Viscosity	40% 102-103	ASTM D 562
Solids, %		
• By weight	60	ASTM D 5201
• By volume	40	
Gloss	3.0	ASTM D 523
Light reflectance, %	> 91	ASTM E 1347
Resistance to wind-driven rain	Meets requirement – no water penetration	TT-C-555B
Flexibility 1" mandrel	No cracking	ASTM D 522
Impact resistance, in-lbs		
• Direct	82	ASTM D 2794
• Reverse	78	
Fungus resistance	No growth; meets requirement	ASTM D 3273
Adhesion on concrete Adhesion on steel	6.5 N/mm ² 6.3 N/mm ²	-
CO ₂ Diffusion Strength	High	-
Chloride ion coefficient	NO chloride ion diffusion was observed. After 130 days of plunging	-
Freezing / Thawing	No effect was observed	-
Dry Time at 20° C	25 minutes	-

SURFACE PREPARATION

- Surfaces should be clean and sound and free of all bond-inhibiting contaminants.
- Concrete substrates should be fully cured.
- Repair any holes, spalled and damaged concrete with appropriate repair materials. Allow appropriate cure time prior to coating.
- Remove any protruding concrete accessories and smooth out any surface irregularities.

DRYING TIME

Times assume (21° C) and 50% relative humidity.

- To touch: 1–2 hours
- To recoat: minimum of 6 hours

Lower surface or air temperatures and higher relative humidity will extend the drying time.

ROOFCRYL

Acrylic Protective Coating

PRE-CAUTION

- Do not apply when substrate or ambient temperature is (4° C) or below or is expected to fall below (4° C) within 24 hours after application.
- Do not apply if rain is expected within 24 hours of application.

HEALTH, SAFETY AND ENVIRONMENT

All safety measures should be observed during application. Fire extinguishers should be available at site. Care should be taken with gas, and torch should not be rested on finished surface or on any materials that can be scratched by flame or hot torch. Gloves and goggles should be worn by all workers during application.

Read, understand and follow all Material Safety Data Sheets and product label information for this product prior to use.

TECHNICAL SUPPORT

International Insulation Company (IIC) - Bitugulf technical support team consist of expert engineers offers a comprehensive service support to specifiers, end users and contractors, and on-site technical assistance.

MIXING

Prior to use, mix Roofcryl at slow speed with drill and mixing paddle to ensure uniform color and to minimize air entrapment.

TOOL CLEANING

Clean all tools immediately with clean water.

PACKAGING

18-kg. per pail, white color.

STORAGE

- Keep the products packed in a dry place.
- Keep away from direct sunlight.
- Do not place the pallets on top of each other.
- Rolls must always be kept in a vertical position.



INTERNATIONAL INSULATION COMPANY (BITUGULF)

Factory

Western Shuaiba Industrial, Block (3), Building (90),
Opposite of Kuwait Steel Co.

Telephone: (+965) 23262822, 9660 0332

Fax: (+965) 23262825

Email: info@knimco.com

Showroom

Shuwaikh Industrial, Block (A), Building (139),
Opposite to Hyundai Maintenance Center

Telephone: (+965) 24912765, 94122711

Fax: (+965) 24912776

Email: shwrm@knimco.com

Website: www.knimco.com